



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ³ :		A1	(11) International Publication Number: WO 80/01232 (43) International Publication Date: 26 June 1980 (26.06.80)		
(21) International Application Number: PCT/EP79/00101		(74) Agent: LEON, Alain, Elie; Unilever N.V., Patent Division, P.O. Box 137, 3130 AC Vlaardingen (NL).			
(22) International Filing Date: 18 December 1979 (18.12.79)		(81) Designated States: JP, US.			
(31) Priority Application Number: 78.12335		Published <i>With international search report</i>			
(32) Priority Date: 20 December 1978 (20.12.78)					
(33) Priority Country: NL					
(71) Applicant <i>(for JP only)</i> : UNILEVER, N.V. [NL/NL]; Burg. s'Jacobplein 1, 3000 DK Rotterdam (NL).					
(72) Inventors; and					
(75) Inventors/Applicants <i>(for US only)</i> : REK, Johannes, Henricus, Maria [NL/NL]; Coornhertstraat 96, 3132 GK Vlaardingen (NL). HOLEMANS, Pieter Maria, Jozef [BE/BE]; Schapendreef 3, 2070 Ekeren (BE).					

(54) Title: PROCESS FOR PRODUCING A MARGARINE

(57) Abstract

An improved process for producing a margarine having a reduced tendency to spattering, the improvement consisting of adding separately to the oil phase effective proportions of a phosphatide and a finely divided hydrophilic metal-and/or metalloid oxide.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT

AT	Austria	LU	Luxembourg
BR	Brazil	MC	Monaco
CF	Central African Republic	MG	Madagascar
CG	Congo	MW	Malawi
CH	Switzerland	NL	Netherlands
CM	Cameroon	RO	Romania
DE	Germany, Federal Republic of	SE	Sweden
DK	Denmark	SN	Senegal
FR	France	SU	Soviet Union
GA	Gabon	TD	Chad
GB	United Kingdom	TG	Togo
JP	Japan	US	United States of America

A process for producing a margarine

The present invention relates to a process for producing a margarine having a reduced tendency to spattering.

When margarine is used for baking, the water vaporized as soon as
5 the margarine has melted, and spattering occurs then to a serious degree. If no precautions are taken, the droplets of water in the margarine flow together on being heated and the larger droplets thus formed then get overheated and explode. This spattering can be reduced by the addition of, for example, lecithin or thermostable
10 emulsifiers, as a result of which the flowing together of the droplets of water is prevented and a calmer baking picture emerges. However, the desired anti-spattering behaviour is not always obtained to a sufficient degree with such so-called anti-spattering agents. Lecithin, for example, only produces a very weak anti-
15 spattering effect on non-salted milk margarines.

According to a process described in Netherlands patent application No. 7314936 a margarine having a reduced tendency to spattering is produced by incorporating in the oil phase a finely divided metal-
20 or metalloid oxide which was pre-treated with alcohols, fatty acids, aldehydes or lecithins in order to render the oxide hydrophobic. Specific examples mentioned in this publication are methylated silicon dioxide and lecithinated silicon dioxide. A drawback associated to the use of this method is that the anti-spattering
25 effect achieved, diminishes on storage as time goes by as shown in a test illustrated in Example 19 of said Netherlands patent application.

Applicants have found a process which alleviates the above
30 disadvantage to a great extent.

The improved process according to the invention for producing a water-in-oil emulsion of the margarine type, which displays a reduced tendency to spattering consists of adding separately
35 (a) a phosphatide and (b) a hydrophilic finely divided metal-



and/or metalloid oxide, into an oil phase essentially consisting of a fat or fat blend which is appropriate for producing a non-liquid margarine.

5 It is an essential feature of the present invention that the phosphatide and the oxide components are added separately to the oil phase. By added "separately" is meant that both components are physically separated before and during their incorporation in the oil phase and that a possible interaction between the components
10 can consequently only occur in situ in the oil phase.

The effect achieved by adding separately both the phosphatide and the hydrophilic oxide was very surprising since addition of either only the phosphatide or only the hydrophilic oxide results in
15 a very unsatisfactory anti-spattering behaviour. (Vide in this context the table of Examples 6-17 of NL 7314936 and the comparative Examples 10, 13, 15 and 17).


20 Suitable phosphatides which are preferred are those phosphatides which are obtained by treating vegetable oils in which phosphatides are present, such as soya oil, groundnut oil, sunflower oil and rapeseed oil, cottonseed oil, and the like, with steam or water and separating out the phosphatides, which are also less accurately referred to as lecithin. Naturally, phosphatides of other origin,
25 such as egg-yolk, or synthetically prepared phosphatides can also be used for the process according to the present invention. Further, partly hydrolysed phosphatides (i.e. phosphatides of which in at least a part of the molecules present an acyl group of the diacyl-glycerophosphatides has been split off), hydroxylated phosphatides
30 and/or acylated phosphatides can be used in the process according to the invention. Also suitable are phosphatides obtained from fractionation of the above-mentioned phosphatides with a solvent or mixtures of solvents.

35 The phosphatides are usually added in an amount of about 0.01 to about 5% by weight, preferably between about 0.1 and about 1% by weight, based on the weight of the margarine.

The finely divided metal- and/or metalloid oxide useful for use in the process of the present invention are well-known substances. They are normally prepared by thermal decomposition (vapour phase hydrolysis) of the corresponding volatile metal and metalloid halogenides at very high temperatures (about 1100°C), the particle size and the surface area of the oxides obtained being regulated by means of the concentration of the halogenides, the temperature and the reaction time. The bulk density is regulated by the degree of compression of the oxides obtained. These highly voluminous oxides are commercially available, for example from Joseph Crosfield and Sons, of Warrington, England, and from Degussa, in Germany, under the trade-mark "Aerosol"®. Suitable highly voluminous silicon dioxide, aluminium oxide and mixtures thereof are sold under this name. In the U.S.A. such a product, having the trade-mark "Cab-O-Sil", is sold by Cabot, Inc. Highly voluminous silicon dioxide can also be prepared by the so-called precipitation method, for example by adding an alkali metal silicate solution and an acid solution to water at about 50°C, keeping the pH constant, and subsequently washing, filtering and drying the precipitate.

By controlling the concentration of the reactants, the reaction time, the temperature and the pH, silicon dioxides having certain surface areas and particle sizes are obtained. Highly voluminous aluminium oxide, silicon dioxide and iron oxide can likewise be prepared with the aid of vapour phase hydrolysis, as also titanium dioxide and zirconium oxide. Also mixtures of these oxides are prepared by vapour phase hydrolysis of the corresponding mixture of halogenides. Highly voluminous magnesium oxide can be prepared by calcination of magnesium hydroxide, magnesium oxalate or basic magnesium carbonate at about 600°C, followed by rapid cooling over a desiccating agent, such as phosphorous pentoxide. Highly voluminous magnesium oxide is commercially available, for example from the Chemical and Insulating Cy Ltd, Darlington, Durham, England, under the trade-mark "Darlington Magnesium Oxyd LMO/100". The oxide preferably used is highly voluminous, light silicon dioxide having the physical characteristics specified above.

Mixtures of highly voluminous metal and metalloid oxides, for example a mixture of silicon dioxide and aluminium oxide, can also be used.



Applicants have found that useful hydrophilic oxides should preferably have (a) a specific surface area of at least 130 m²/g. and preferably a specific surface area ranging from 200-400 m²/g and (b) a particle size ranging from 1-100 μ .

5

The preferred average primary particle size ranges from 5-30 μ . The average surface area can be determined by the method of Brunauer et al. (J.Am.Chem.Soc. 60 (1938) p. 309).

10 Suitable proportions of the hydrophilic oxide can be assessed in each particular case. Applicants have surprisingly found that in most instances proportions as low as ranging from 0.025 - 0.15 wt% will suffice. The preferred proportions lie between 0.05 and 0.10% by weight based on the weight of the
15 margarine.

The margarines prepared according to the invention can be salt-free or salted milk margarines, as well as salted or non-salted water margarines.

20

The invention is particularly concerned with non liquid margarines or plastic margarines. By this term is meant margarines having an oil phase essentially consisting of a fat or fat blend which has a slip melting point ranging from 30-40°C.

25

The proportion of oil phase in the margarine lies normally within 75-90% by weight and the proportion of the aqueous phase lies within the range of 10-25% by weight.

30 Applicants have further found that the particularly good anti-spattering effect could be achieved by ensuring that the pH of the aqueous phase ranges from 4.0-6.5 .

35 The margarines produced according to the invention may include additives such as flavours, vitamins, anti-oxidants and the like. The margarines can be produced using techniques known per se and in this connection reference is made to the book "Margarine" by Andersen & Williams 1965.

The invention will now be illustrated in the following Examples.

Example 1

With the aid of a Votator a margarine was prepared in the usual manner
5 starting from 83.786% by weight of a fatty phase consisting of 20
parts coconut oil, 15 parts palm kernel oil, 15 parts palm oil,
50 parts soya oil, hydrogenated to a melting point of 32°C
(D₀ = 800, D₁₅ = 550, D₂₀ = 450, D₂₅ = 250, D₃₀ = 125, D₃₅ < 25)
and 16% of an aqueous phase consisting of 50% of buttermilk and
10 50% of water (pH = 4.6).

Before the fatty phase was emulsified with the aqueous phase, the
following were added separately to the fatty phase: 0.168% by weight
of raw soya phosphatide (that consisted for about 1/3 of soya
15 oil) and 0.168% by weight of Aerosil 200 (finely divided silicon
dioxide having a surface area of 200 m²/gram and an average primary
particle size of 16 µ).

This margarine was subjected after 3 and 10 days storage to the following
20 spattering test: in an enamelled pan with a smooth bottom surface
50 g of the margarine was heated each time to 175°C (regulated
by a thermocouple). The spattering fat was caught, at a distance
of 21 cm above the pan, on a piece of paper that had been weighed
beforehand. After the test the piece of paper was weighed again.
25 The degree of spattering was determined on the basis of the increase
in the weight of the paper and this was converted as follows into
an assessment according to points:

10 = very good anti-spattering behaviour = less than 10 mg
6 = moderate anti-spattering behaviour = 50-100 mg
30 2 = very bad anti-spattering behaviour = > 500 mg.

The points in between express a corresponding spattering behaviour.
The results were as follows:

after 3 days storage: 10
35 after 10 days storage: 10.

When the test was repeated under identical conditions, but with, as



only difference, the oxide first having been mixed with the phosphatide before it was added to the fatty phase, the results of the spattering test were:

after 3 days storage: 9.5
5 after 10 days storage: 6.

Example 2

A margarine was prepared having the same fat mixture and the same aqueous phase as in Example 1, and was subsequently subjected to 10 the same spattering test. This time, however, 0.164% by weight of raw soya phosphatide and 0.05% by weight of Aerosil 300 were added separately to the fatty phase. (Aerosil 300 has a surface area of $300 \text{ m}^2/\text{gram}$ and an average particle size of 8μ).

15 The results of the spattering tests were:

after 2 days storage: 10
after 5 days storage: 9
after 11 days storage: 9.5.

20 When the test was repeated under identical conditions, but with, as only difference, the oxide first having been mixed with the phosphatide before it was added to the fatty phase, the results of the spattering test were:

after 2 days storage: 5
25 after 5 days storage: 6
after 11 days storage 5.

Example 3

The procedure of Example 1 was repeated, excepted that 0.1% by weight 30 MgO (specific area $180 \text{ m}^2/\text{gram}$ average primary particle size 86 milimicrons) was used. After a storage period of 10 days the anti-spattering behaviour was as satisfactory as in Example 1.

C L A I M S

1. An improved process for producing a water-in-oil emulsion of the margarine-type which displays a reduced tendency to spattering, by (a) incorporating in the oil phase a phosphatide and a finely divided metal- and/or a metalloid oxide, and (b) working up the oil- and the aqueous phase to produce a margarine, the improvement consisting of adding a hydrophobic finely divided metal- and/or metalloid oxide and said phosphatide separately in an oil phase essentially consisting of a fat or fat blend which is appropriate for producing a non-liquid margarine.
10
2. A process according to claim 1, in which the oil phase consists of a fat or fat blend having a slip melting point ranging from 30-40°C.
15
3. A process according to claim 1, in which a hydrophilic metal- or metalloid oxide is used which has a specific surface area of at least 130 m²/gram.
20
4. A process according to claim 3, in which a hydrophilic oxide is used which has a specific surface area ranging from 200-400 m²/gram.
25
5. A process according to claim 3 in which the particle size of the hydrophilic oxide ranges from 1 to 100 m μ .
30
6. A process according to claim 3, in which the average primary particle size of the hydrophilic material ranges from 5-30 m μ .
35
7. A process according to claim 1, in which 0.025 to 0.15% by weight of hydrophilic oxide is incorporated in the oil phase.
8. A process according to claim 1, in which the hydrophilic oxide consists of silicon dioxide, aluminium oxide and/or magnesium oxide.



9. A process according to claim 1, in which 0.01 to 5% by weight phosphatide is used.

10. A process according to claim 1, in which the oil phase is
5 mixed with an aqueous phase having a pH ranging from 4.0-6.5.

INTERNATIONAL SEARCH REPORT

International Application No PCT/EP 79/00101

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ³

According to International Patent Classification (IPC) or to both National Classification and IPC

Int.Cl. ³ A 23 D 3/00

II. FIELDS SEARCHED

Minimum Documentation Searched ⁴

Classification System	Classification Symbols
Int.Cl. ³	A 23 D 3/00; A 23 D 5/00

Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁵

III. DOCUMENTS CONSIDERED TO BE RELEVANT ¹⁴

Category ⁶	Citation of Document, ¹⁵ with indication, where appropriate, of the relevant passages ¹⁷	Relevant to Claim No. ¹³
	NL, A, 7314935, published June 18, 1974 see examples 11-36, Unilever N.V. --	1,2-9
A	NL, A, 7314936, published June 18, 1974 Unilever N.V. --	
A	NL, A, 262880, published May 25, 1964 Unilever N.V. --	
A	FR, A, 2049113, published March 26, 1971 The Procter & Gamble Co. -----	

* Special categories of cited documents: ¹⁸

"A" document defining the general state of the art

"E" earlier document but published on or after the international filing date

"L" document cited for special reason other than those referred to in the other categories

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but on or after the priority date claimed

"T" later document published on or after the international filing date or priority date and not in conflict with the application, but cited to understand the principle or theory underlying the invention

"X" document of particular relevance

IV. CERTIFICATION

Date of the Actual Completion of the International Search:

20th March 1980

Date of Mailing of this International Search Report:

15th April 1980

International Searching Authority:

European Patent Office

Signature of Authorized Officer ²⁰

G.L.M. Kruydenberg